

LOCTITE[®] 3D 3820™

February 2020

PRODUCT DESCRIPTION

LOCTITE[®] 3D 3820™ provides the following product characteristics:

Technology	Stereolithography Resin
Appearance	Clear light blue liquid ^{LMS}
Chemical Type	Acrylic
Odor	Mild
Cure	Ultraviolet (UV) / Visible light
Viscosity	Low
Application	Functional Prototyping
Product Benefits	<ul style="list-style-type: none"> • Good print resolution • Short exposure time • High clarity

LOCTITE[®] 3D 3820™ is a clear light curing acrylic resin that may be used for functional prototyping via stereolithography. LOCTITE[®] 3D 3820™ cures with very short exposure to monochromatic light sources such as LED or Laser. Printed articles made from LOCTITE[®] 3D 3820™ exhibit good print resolution and high optical clarity. LOCTITE[®] 3D 3820™ is a low viscosity liquid that is printable at room temperature across various Laser SLA and DLP Platforms.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C, g/cm ³	1.1
Flash Point - See SDS	
Viscosity, Cone & Plate, mPa*s (cP): Temperature: 25C, Shear Rate: 200 s-1	600 to 1,400 ^{LMS}

TYPICAL CURING PERFORMANCE

LOCTITE[®] 3D 3820™ can be cured by exposure to ultraviolet and visible light of sufficient intensity and wavelength. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of the light source, exposure time and light transmittance of the printer window through which the light must pass.

LOCTITE[®] 3D 3820™ will cure with DLP and Lasers ranging from 300 to 450 nm.

The following working curve values were determined using a DLP printer at 405nm wavelength;

Cure Properties

Critical Exposure (Ec) , mJ/cm ²	24.3
Penetration Depth (Dp) , mm	0.246

TYPICAL PROPERTIES OF CURED MATERIAL

All data is recorded on specimens printed in the XY plane at 0.050mm layer thickness on a DLP printer at 405nm. Some variation is expected when printing in the Z plane. The physical properties in the table below are reflective of what one may observe under the noted conditions. Contact your local Henkel Technical Service team for further information.

Physical Properties

AS PRINTED:

Elongation, at break, ASTM D638, %		45 to 49
Tensile Strength, ASTM D638	MPa (ksi)	17 to 19 (2.5 to 2.8)
Tensile Modulus, (Secant 0.002), ASTM D638	MPa (ksi)	370 to 450 (54 to 65)
Notched IZOD Impact, ASTM D256 J/m		33 to 40

Physical Properties

POST PROCESSED:

Samples were exposed for 100 seconds per side at 100% intensity using a Loctite[®] CL36™ cure chamber.

Elongation, at break, ASTM D638, %		26 to 46
Tensile Strength, ASTM D638	MPa (ksi)	18 to 28 (2.6 to 4.1)
Tensile Modulus, (Secant 0.002), ASTM D638	MPa (ksi)	520 to 840 (75 to 122)
Notched IZOD Impact, ASTM D256 J/m		31 to 37
Volume Shrinkage, %		7.5
Linear Shrinkage, ASTM D 792, %		2.6
Hardness (Shore D), ASTM D2240		60

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions For Use:

1. This product is light sensitive; exposure to daylight, UV light and artificial lighting should be kept to a minimum during storage and handling.
2. Stir well before using..
3. Post print processing:
rinse the printed part using an approved cleaner to remove uncured resin.
If desired, the clarity of the printed part can be improved by coating the printed part with a thin layer of Loctite® 3D 3820™ then exposing it for 100 seconds per side at 100% intensity using a Loctite® CL36™ cure chamber.

Loctite Material Specification^{LMS}

LMS dated July 25, 2018. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
µm / 25.4 = mil
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·m x 0.738 = lb·ft
N·mm x 0.142 = oz·in
mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0